ΠΤΙΠ ΓΙΙΓ ΠΛΠ"

④

AD-A212 105

OFFICE OF NAVAL RESEARCH

Contract N00014-86-K-0043

TECHNICAL REPORT No. 109

Gap States of Charged Solitons in Polyacetylene

by

Xin Sun, Dingwei Lu, Rouli Fu, D. L. Lin and Thomas F. George

/

Prepared for Publication

in

Physical Review B

Departments of Chemistry and Physics
State University of New York at Buffalo
Buffalo, New York 14260

August 1989

DTIC
S ELECTF
SEP 11 1989
(*) **B** **D**

89 9 8 097

REPORT DOCUMENTATION PAGE		Form Approved OMB No. 0704-0188

1a. REPORT SECURITY CLASSIFICATION Unclassified	1b. RESTRICTIVE MARKINGS

2a. SECURITY CLASSIFICATION AUTHORITY	3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release; distribution unlimited
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE	

4. PERFORMING ORGANIZATION REPORT NUMBER(S) UBUFFALO/DC/89/TR-109	5. MONITORING ORGANIZATION REPORT NUMBER(S)

6a. NAME OF PERFORMING ORGANIZATION Depts. Chemistry & Physics State University of New York	6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION

6c. ADDRESS (City, State, and ZIP Code) Fronczak Hall, Amherst Campus Buffalo, New York 14260	7b. ADDRESS (City, State, and ZIP Code) Chemistry Program 800 N. Quincy Street Arlington, Virginia 22217

8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER Contract N00014-86-K-0043

8c. ADDRESS (City, State, and ZIP Code) Chemistry Program 800 N. Quincy Street Arlington, Virginia 22217	10. SOURCE OF FUNDING NUMBERS			
	PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.	WORK UNIT ACCESSION NO.

11. TITLE (Include Security Classification)

Gap States of Charged Solitons in Polyacetylene

12. PERSONAL AUTHOR(S) Xin Sun, Dingwei Lu, Rouli Fu, D. L. Lin and Thomas F. George

13a. TYPE OF REPORT	13b. TIME COVERED FROM _____ TO _____	14. DATE OF REPORT (Year, Month, Day) August 1989	15. PAGE COUNT 17

16. SUPPLEMENTARY NOTATION

17.	COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)
FIELD	GROUP	SUB-GROUP	POLYACETYLENE, POLYMERS, DEEP AND SHALLOW LEVELS,
			GAP STATES, CONDUCTION AND VALENCE BANDS,
			CHARGED SOLITONS, ABSORPTION SPECTRA. (JES)

19. ABSTRACT (Continue on reverse if necessary and identify by block number)

By considering the electron interactions in polyacetylene, it is found that there exist two gap states in charged solitons of trans-polyacetylene: one is deep level, and the other is shallow level. The deep one shifts 0.23 eV down (for a positive soliton) or up (for a negative soliton) from the center of the gap, while the shallow one is 0.06 eV under the bottom edge of the conduction band (positive soliton) or above the top edge of the valence band (negative soliton). These results agree with the absorption spectra of trans-polyacetylene. Other shallow states outside the energy bands are also predicted.

20. DISTRIBUTION/AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☒ SAME AS RPT. ☐ DTIC USERS	21. ABSTRACT SECURITY CLASSIFICATION Unclassified
22a. NAME OF RESPONSIBLE INDIVIDUAL Dr. David L. Nelson	22b. TELEPHONE (Include Area Code) (202) 696-4410	22c. OFFICE SYMBOL

DD Form 1473, JUN 86   Previous editions are obsolete.   SECURITY CLASSIFICATION OF THIS PAGE

Gap states of charged solitons in polyacetylene

Xin Sun and Dingwei Lu
Center of Theoretical Physics
Chinese Center of Advanced Science and Technology (World Laboratory)
Beijing 100080

and

Laboratory of Solid State Microstructures
Nanjing University
Nanjing

and

Department of Physics
Fudan University
Shanghai 100433, People's Republic of China *

Rouli Fu
Laboratory of Infrared Physics
Shanghai Institute of Technical Physics
Academia Sinica
Shanghai, People's Republic of China

D. L. Lin and Thomas F. George [†]
Department of Physics and Astronomy
State University of New York at Buffalo
Buffalo, New York 14260

Abstract

By considering the electron interactions in polyacetylene, it is found that there exist two gap states in charged solitons of trans-polyacetylene: one is deep level, and the other is shallow level. The deep one shifts 0.23 eV down (for a positive soliton) or up (for a negative soliton) from the center of the gap, while the shallow one is 0.06 eV under the bottom edge of the conduction band (positive soliton) or above the top edge of the valence band (negative soliton). These results agree with the absorption spectra of trans-polyacetylene. Other shallow states outside the energy bands are also predicted.

1988 PACS Nos.:   71.50.+t, 71.38.+i, 71.90.+q

* Mailing address

† Also affiliated with the Department of Chemistry and the Center for Electronic and Electro-optic Materials, State University of New York at Buffalo.

I. Introduction

The most novel concept in conducting polymers is perhaps the soliton carrier with reversed relation between charge and spin, that is, the charged soliton does not have spin, but the neutral soliton has spin 1/2.[1] Studying various properties of the soliton is important for understanding many peculiar traits of conducting polymers.[2] One topic is the electron states of the soliton, especially the bound states trapped by the soliton. Trans-polyacetylene possesses two-fold degenerate dimerized ground states, phase A and phase B. When a chain of tran-polyacetylene contains phase A in some part of the chain and phase B in the rest, a domain wall appears between phases A and B, which is the soliton. Within phase A or phase B, atoms are arranged in a periodically dimerized lattice in which electrons move in extended states. In the region of the domain wall, however, the atomic distribution deviates from the periodic structure of the dimerization and produces a distortion potential on electrons. Then the electron can be trapped by this distortion potential to form bound states around the soliton. The levels of these bound states are located in the gap, which is the skeleton picture for the origin of gap states. The problem is to determine how many bound states can exist around the soliton and where are the locations of their levels. A simple Hamiltonian to show the soliton is the Su, Schrieffer and Heeger (SSH) model,[1] in which the electron-electron interaction is neglected. Based on the electron-lattice interaction alone (the SSH model), it is well known that there exists a mid-gap state in the electron spectrum of the soliton. The level of this bound state sits at the center of the gap. The question is whether there are any other gap states. We attempt to answer this question in the present paper.

The difficulty with the SSH model is that it can not be solved analytically. In order to get a rigorous solution of the soliton, Takayama, Lin-Liu and Maki (TLM) have introduced the continuum model[3] which can be solved analytically. For the TLM model it has been rigorously proven that the soliton has one and only one electron bound state, which sits at the middle of the gap. Since then, people have tended to think that the soliton has only one gap state. Experimentally, both the dopant-induced absorption[4] and the photo-induced absorption[5] in trans-polyacetylene have shown a second absorption peak whose energy is about half of that of the main peak. It provides the evidence for the gap state of a soliton produced by the dopants or the incident photons. Absorption spectra actually indicate that the energy of the second peak is not exactly equal to one half of the gap, but is about 0.25 eV smaller than half of the gap. It means that the level of the gap state is shifted from the center of the gap. Such a shift is caused by the electron-electron repulsion,[6] which has to be considered before a reliable answer can be obtained about the number and locations of bound states of the soliton.

It should also be pointed out that the TLM model is a continuum model in which the molecular structure of the polymer chain has been smeared out. However, the real polymer chain consists of discrete atoms. The continuum approximation made in the TLM model may have lost some bound states existing in the chain with discrete structure. In fact, an earlier work using the SSH model has revealed that the discrete structure can possess some shallow electron bound states if the electron-lattice coupling is strong enough.[7] On the other hand, the photo-induced absorption spectrum demonstrates that there is a cusp sitting on the left-hand side of the main absorption peak.[5] The separation between the cusp and the top of the main peak is about 0.06 eV.

Such structure in the absorption spectrum also indicates that there is a level near the band edge. Therefore, both the theory and the experiment suggest that there are some other bound states in the gap. In order to find a definite answer, we must include both the electron-lattice and electron-electron interactions in our investigations of the electron spectrum of the soliton and consider the discrete structure of the chain.

II. Theoretical formulation

As usual, the electron-lattice and electron-electron interactions are described by the SSH model H_0 and Hubbard model H',

$$H_0 = t_0 \left(-\sum_{n,s} [1 + (-1)^n \phi_n] (c^\dagger_{n+1,s} c_{n,s} + c^\dagger_{n,s} c_{n+1,s}) + \frac{1}{\lambda \pi} \sum_n \phi_n^2 \right) \quad , \quad (1)$$

$$H' = (U/2) \sum_{n,s} c^\dagger_{n,s} c_{n,s} c^\dagger_{n,-s} c_{n,-s} \quad , \quad (2)$$

and the total Hamiltonian is

$$H = H_0 + H' \quad , \quad (3)$$

where t_0 is the hopping constant, λ is the electron-lattice coupling constant, ϕ_n is the dimensionless displacement of lattice, $c^\dagger_{n,s}$ and $c_{n,s}$ are creation and annihilation operators, respectivley, of an electron on site n with spin s, and U is the strength of the electron interactions. In the case of polyacetylene,

$$t_0 = 2.5 \text{ eV} \quad , \quad \lambda = 0.2 \quad , \quad U = 5 \text{ eV} \quad . \quad (4)$$

In the Hartree-Fock approximation, the eigenequation of Hamiltonian (3) is

$$\epsilon^s_\mu Z^s_{n,\mu} = - t_0[1 + (-1)^n(\phi_n + \phi_{n+1})]Z^s_{n+1,\mu}$$

$$- t_0[1 + (-1)^{n-1}(\phi_n + \phi_{n-1})]Z^s_{n-1,\mu} + UX_{n,s}Z^s_{n,\mu} \quad . \tag{5}$$

where ϵ^s_μ and $Z^s_{n,\mu}$ are the eigenenergy and wave function of the electron in the eigenstate μ with spin s, and

$$X_{n,s} = <c^\dagger_{n,-s}c_{n,-s}> \tag{6}$$

is the self-consistent ground-state average of the electron occupation at site n with spin -s. The lattice displacement ϕ_n is determined by minimizing the total energy,

$$\phi_n + \phi_{n+1} = \pi\lambda(-1)^n[\sum_{\substack{\mu,s \\ (occ.)}} Z^s_{n,\mu}S^s_{n+1,\mu} - \frac{1}{N}\sum_n\sum_{\substack{\mu,s \\ (occ.)}} Z^s_{n,\mu}Z^s_{n+1,\mu}] \quad .$$

$$\tag{7}$$

Combining Eqs. (5), (6) and (7), and the energy spectrum ϵ^s_μ and wave function $Z^s_{n,\mu}$ of the electron can be obtained by solving these closed equations numerically. In our calculation, we take a chain with 201 atoms. For charged solitons, each level is either doubly occupied (negative soliton) or empty (positive soliton). In this case, the electron states are spin independent:

$$Z^s_{n,\mu} = Z^{-s}_{n,\mu} \quad \text{and} \quad \epsilon^s_\mu = \epsilon^{-s}_\mu \quad . \tag{8}$$

III. Results and discussion

The energy spectra of positive and negative solitons are shown in Figs. 1 and 2, respectivley. There are two gap states: deep level ϵ_d and shallow level ϵ_s. The deep level does not sit at the center of the gap, but shifts 0.23 eV down (positive soliton) or up (negative soliton) from the center of the gap. The shallow level is 0.06 eV beneath the bottom edge of conduction band (positive soliton) or above the top edge of valence band (negative soliton).

For the case of a positive soliton (Fig. 1), both deep and shallow levels are empty, and the electrons in the valence band can be excited into higher levels. There are three ways to make a transition: (1) going to the conduction band, which corresponds to the main absorption peak; (2) going to the deep level ϵ_d, which is the second absorption peak, whose energy is 0.23 eV smaller than half of the gap, and which agrees with the dopant and photo-induced absorption; and (3) going to the shallow level ϵ_s, forming a cusp which is separated by 0.06 eV from the top of the main peak. The photo-induced absorption[3] has shown evidence of such a cusp.

For the case of a negative soliton (Fig. 2), both deep and shallow levels are occupied. There are also three transitions: (1) from the valence band to the conduction band, which is the main absorption peak; (2) from a deep level ϵ_d to the conduction band, which is the second absorption peak; and (3) from a shallow level ϵ_s to the conduction band, which is the cusp. The frequencies of these three transitions are exactly the same as those of a positive soliton.

The wave functions $Z_{n,\sigma}$ and $Z_{n,d}$ of the shallow and deep levels are shown in Fig. 3. As expected, the width of the wave function $Z_{n,d}$ of the deep level is smaller than that of the wave function $Z_{n,s}$ of the shallow level.

Based on the above results, we can theoretically give a schematic absorption spectrum for the charged solitons shown in Fig. 4, where three features appear: (1) the main peaks, (2), the second peak and (3) the shoulder. These features correspond to three absorption lines with some uncertain broadenings. The strength and broadening of these absorption lines depend on the density of solitons and the interaction between the solitons and the surroundings. Further study is needed in order to obtain more details. Apparently, the skeleton features of our theoretical absorption spectrum are in accord with the photo-induced absorption.[5] In the dopant absorption, besides the main peak and the second peak, there also appears a shoulder near the main peak.[4]

It should be mentioned that there are two more shallow levels ϵ'_s and ϵ''_s sitting outside the bands. For a positive soliton, these two shallow levels are underneath the bottom edge of the valence band (see Fig. 1). For a negative soliton, they are above the top edge of the conduction band (see Fig. 2). The wave functions of these two shallow levels are shown in Fig. 5. These two shallow levels will give more features of the absorption spectrum in the energy region of 5-6 eV. It is therefore of great interest to carry out experiments to observe the absorption spectrum in that energy region.

References

1. W. P. Su, J R. Schrieffer and A. J. Heeger, Phys. Rev. Lett. 42, 1698 (1979); Phys. Rev. B 22, 2099 (1980).

2. T. A. Skotheim, Ed., Handbook of Conducting Polymers (Marcel Dekker, New York, 1986).

3. H. Takayama, Y. R. Lin-Liu and K. Maki, Phys. Rev. B 21, 2388 (1980).

4. J. Tanaka and M. Tanaka, in Handbook of Conducting Polymers, Vol. 2, ed. by T.A. Skotheim (Marcel Dekker, New York, 1986), p. 1269 ff.

5. J. Orenstein, Z. Vardeny and G. L. Baker, J. Phys. Paris Colloq., C3, 44, 407 (1983).

6. K. R. Subbaswamy and M. Grabowski, Phys. Rev. B 24, 2168 (1981); S. Kivelson and D. E. Heim, Phys. Rev. B 26, 4278 (1982).

7. R. Fu, Z. Shuai, J. Liu, X. Sun and J. C. Hicks, Phys. Rev. B 38, 6298 (1988).

Figure Captions

1. Energy spectrum of an electron in a positive soliton.

2. Energy spectrum of an electron in a negative soliton.

3. Electron wave functions of a deep gap state $Z_{n,d}$ and shallow gap state $Z_{n,s}$.

4. Schematic absorption spectrum for the charged solitons.

5. Electron wave functions of two outside shallow states $Z'_{n,s}$ and $Z''_{n,s}$.

$C\,B$

$\mathcal{E}_s$ 0.06 eV

1   3

$\mathcal{E}_d$ 0.23 eV

2

$V\,B$

$\mathcal{E}_s'$ 0.11 eV

$\mathcal{E}_s''$

Fig. 1

$\mathcal{E}_s''$

$\mathcal{E}_s'$ ———————— $\updownarrow$ 0.11 eV

C.B

2 | 3

$\mathcal{E}_d$ ———•——•———

$\updownarrow$ 0.23 eV

1

$\mathcal{E}_s$ ———•——•——— $\updownarrow$ 0.06 eV

V.B

Fig. 2

Fig. 3

absorption

(arb. unit)

2

3 1

0.4   0.8   1.2 (eV)   h.ν

Fig. 4.

Fig. 5

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	No. Copies		No. Copies
Office of Naval Research Attn: Code 1113 800 N. Quincy Street Arlington, Virginia 22217-5000	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Couda Naval Weapons Support Center Code 50C Crane, Indiana 47522-5050	1	Naval Weapons Center Attn: Dr. Ron Atkins Chemistry Division China Lake, California 93555	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko, Code L52 Port Hueneme, California 93401	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12 high quality	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
DTNSRDC Attn: Dr. H. Singerman Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375-5000	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1
		Dr. David L. Nelson Chemistry Division Office of Naval Research 800 North Quincy Street Arlington, Virginia 22217	1

ABSTRACTS DISTRIBUTION LIST, 056/625/629

Dr. J. E. Jensen
Hughes Research Laboratory
3011 Malibu Canyon Road
Malibu, California 90265

Dr. J. H. Weaver
Department of Chemical Engineering
  and Materials Science
University of Minnesota
Minneapolis, Minnesota 55455

Dr. A. Reisman
Microelectronics Center of North Carolina
Research Triangle Park, North Carolina
    27709

Dr. M. Grunze
Laboratory for Surface Science and
      Technology
University of Maine
Orono, Maine 04469

Dr. J. Butler
Naval Research Laboratory
Code 6115
Washington D.C. 20375-5000

Dr. L. Interante
Chemistry Department
Rensselaer Polytechnic Institute
Troy, New York 12181

Dr. Irvin Heard
Chemistry and Physics Department
Lincoln University
Lincoln University, Pennsylvania 19352

Dr. K.J. Klaubunde
Department of Chemistry
Kansas State University
Manhattan, Kansas 66506

Dr. C. B. Harris
Department of Chemistry
University of California
Berkeley, California 94720

Dr. F. Kutzler
Department of Chemistry
Box 5055
Tennessee Technological University
Cookesville, Tennessee 38501

Dr. D. DiLella
Chemistry Department
George Washington University
Washington D.C. 20052

Dr. R. Reeves
Chemistry Department
Renssaeler Polytechnic Institute
Troy, New York 12181

Dr. Steven M. George
Stanford University
Department of Chemistry
Stanford, CA 94305

Dr. Mark Johnson
Yale University
Department of Chemistry
New Haven, CT 06511-8118

Dr. W. Knauer
Hughes Research Laboratory
3011 Malibu Canyon Road
Malibu, California 90265

This Document Contains Missing
Page/s That Are Unavailable In
The Original Document

ABSTRACTS DISTRIBUTION LIST, 056/625/629

Dr. G. A. Somorjai
Department of Chemistry
University of California
Berkeley, California 94720

Dr. J. Murday
Naval Research Laboratory
Code 6170
Washington, D.C. 20375-5000

Dr. J. B. Hudson
Materials Division
Rensselaer Polytechnic Institute
Troy, New York 12181

Dr. Theodore E. Madey
Surface Chemistry Section
Department of Commerce
National Bureau of Standards
Washington, D.C. 20234

Dr. J. E. Demuth
IBM Corporation
Thomas J. Watson Research Center
P.O. Box 218
Yorktown Heights, New York 10598

Dr. M. G. Lagally
Department of Metallurgical
  and Mining Engineering
University of Wisconsin
Madison, Wisconsin 53706

Dr. R. P. Van Duyne
Chemistry Department
Northwestern University
Evanston, Illinois 60637

Dr. J. M. White
Department of Chemistry
University of Texas
Austin, Texas 78712

Dr. D. E. Harrison
Department of Physics
Naval Postgraduate School
Monterey, California 93940

Dr. R. L. Park
Director, Center of Materials
  Research
University of Maryland
College Park, Maryland 20742

Dr. W. T. Peria
Electrical Engineering Department
University of Minnesota
Minneapolis, Minnesota 55455

Dr. Keith H. Johnson
Department of Metallurgy and
  Materials Science
Massachusetts Institute of Technology
Cambridge, Massachusetts 02139

Dr. S. Sibener
Department of Chemistry
James Franck Institute
5640 Ellis Avenue
Chicago, Illinois 60637

Dr. Arnold Green
Quantum Surface Dynamics Branch
Code 3817
Naval Weapons Center
China Lake, California 93555

Dr. A. Wold
Department of Chemistry
Brown University
Providence, Rhode Island 02912

Dr. S. L. Bernasek
Department of Chemistry
Princeton University
Princeton, New Jersey 08544

Dr. W. Kohn
Department of Physics
University of California, San Diego
La Jolla, California 92037

ABSTRACTS DISTRIBUTION LIST, 056/625/629

Dr. F. Carter
Code 6170
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. Richard Colton
Code 6170
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. Dan Pierce
National Bureau of Standards
Optical Physics Division
Washington, D.C. 20234

Dr. R. Stanley Williams
Department of Chemistry
University of California
Los Angeles, California 90024

Dr. R. P. Messmer
Materials Characterization Lab.
General Electric Company
Schenectady, New York 22217

Dr. Robert Gomer
Department of Chemistry
James Franck Institute
5640 Ellis Avenue
Chicago, Illinois 60637

Dr. Ronald Lee
R301
Naval Surface Weapons Center
White Oak
Silver Spring, Maryland 20910

Dr. Paul Schoen
Code 6190
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. John T. Yates
Department of Chemistry
University of Pittsburgh
Pittsburgh, Pennsylvania 15260

Dr. Richard Greene
Code 5230
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. L. Kesmodel
Department of Physics
Indiana University
Bloomington, Indiana 47403

Dr. K. C. Janda
University of Pittsburg
Chemistry Building
Pittsburg, PA 15260

Dr. E. A. Irene
Department of Chemistry
University of North Carolina
Chapel Hill, North Carolina 27514

Dr. Adam Heller
Bell Laboratories
Murray Hill, New Jersey 07974

Dr. Martin Fleischmann
Department of Chemistry
University of Southampton
Southampton SO9 5NH
UNITED KINGDOM

Dr. H. Tachikawa
Chemistry Department
Jackson State University
Jackson, Mississippi 39217

Dr. John W. Wilkins
Cornell University
Laboratory of Atomic and
  Solid State Physics
Ithaca, New York 14853

ABSTRACTS DISTRIBUTION LIST, 056/625/629

Dr. R. G. Wallis
Department of Physics
University of California
Irvine, California 92664

Dr. D. Ramaker
Chemistry Department
George Washington University
Washington, D.C. 20052

Dr. J. C. Hemminger
Chemistry Department
University of California
Irvine, California 92717

Dr. T. F. George
Chemistry Department
University of Rochester
Rochester, New York 14627

Dr. G. Rubloff
IBM
Thomas J. Watson Research Center
P.O. Box 218
Yorktown Heights, New York 10598

Dr. Horia Metiu
Chemistry Department
University of California
Santa Barbara, California 93106

Dr. W. Goddard
Department of Chemistry and Chemical
    Engineering
California Institute of Technology
Pasadena, California 91125

Dr. P. Hansma
Department of Physics
University of California
Santa Barbara, California 93106

Dr. J. Baldeschwieler
Department of Chemistry and
  Chemical Engineering
California Institute of Technology
Pasadena, California 91125

Dr. J. T. Keiser
Department of Chemistry
University of Richmond
Richmond, Virginia 23173

Dr. R. W. Plummer
Department of Physics
University of Pennsylvania
Philadelphia, Pennsylvania 19104

Dr. E. Yeager
Department of Chemistry
Case Western Reserve University
Cleveland, Ohio 41106

Dr. N. Winograd
Department of Chemistry
Pennsylvania State University
University Park, Pennsylvania 16802

Dr. Roald Hoffmann
Department of Chemistry
Cornell University
Ithaca, New York 14853

Dr. A. Steckl
Department of Electrical and
  Systems Engineering
Rensselaer Polytechnic Institute
Troy, New York 12181

Dr. G.H. Morrison
Department of Chemistry
Cornell University
Ithaca, New York 14853